




מדינת ישראל  
STATE OF ISRAEL



Ministry of Justice  
Patent Office

משרד המשפטים  
לשכת הפטנטים

This is to certify that  
annexed hereto is a true  
copy of the documents as  
originally deposited with  
the patent application  
of which particulars are  
specified on the first page

זאת לתעודה כי  
רצופים בזה העתקים  
נכונים של המסמכים  
שהופקדו לכתחילה  
עם הבקשה לפטנט  
לפי הפרטים הרשומים  
בעמוד הראשון של  
הנספח.

e annex.

**PRIORITY DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

This 24-06-2003 היום

רשם הפטנטים  
Commissioner of Patents

נתאשר  
Certified

150317

מספר:  
Number

19.06.02

תאריך  
Date

הוקדם.הדחה  
Ante/Post-dated

## בקשה לפטנט

Application for Patent

(אני, (שם המבקש, מענו — ולגבי גוף מאוגד — מקום התאגדותו)  
I (Name and address of applicant, and, in case of a body corporate, place of incorporation)

YISSUM RESEARCH DEVELOPMENT COMPANY  
of the Hebrew University of Jerusalem  
a registered Israeli corporation  
P.O.B. 39135 Givat Ram  
Jerusalem 91390

יישום חברה לפיתוח המחקר  
של האוניברסיטה העברית בירושלים  
חברה ישראלית רשומה  
ת"ד 39135, גבעת רם  
ירושלים 91390

Inventors: Shmuel Yariv, Isaak Lapides, Hagai Peled,  
and Zohar Yermiyahu

הממציאים: שמואל יריב, יצחק לפידוס, חגי פלד  
וזוהר ירמיהו

ששמה הוא  
Owner, by virtue of

הדין

בעל אמצאה מכח  
of an invention, the title of which is:

קומפלקסים אורגנו-חרסית

בעברית  
(Hebrew)

ORGANO-CLAY COMPLEXES

(באנגלית)  
English


Hereby apply for a patent to be granted to me in respect thereof.

מבקש בזאת כי ינתן לי עליה פטנט.

בקשת חלוקה Application for Division	בקשת פטנט מוסף — Application for Patent of Addition	דרישת דין קדימה Priority Claim		
מבקשת פטנט from Application No. _____ מס' _____ Date _____ מיום	לבקשה/לפטנט to Patent/Appl. No. _____ מס' _____ Date _____ מיום	מספר/סימן Number/Mark	תאריך Date	מדינת האיגוד Convention Country
ימיו כח: כללי: צוף בזה P. O. A.: general - attached				
חונש בענין Has been filed in case <u>57024</u>				
המען למסירת הודעות ומסמכים בישראל Address for Service in Israel				
WOLFF, BREGMAN AND GOLLER P. O. Box 1352 Jerusalem, Israel. 91013				
וולף, ברגמן וגולר ת.ד. 1352 ירושלים 91013				

חתימת המבקש  
Signature of Applicant

VOLFF, BREGMAN AND GOLLER

Y: 

2002 שנת 06 בחודש 18 היום  
This of 2002

לשימוש הלשכה  
For Office Use

## ORGANO-CLAY COMPLEXES


קומפלקסים אורגנו-חרסית

The present invention relates to a process for the preparation of a pigment which is an organo-clay complex. More particularly, the present invention relates to the in-situ preparation of azo-dye compounds adsorbed onto clay particles.

Clay minerals are famous for their ability to adsorb organic compounds. Among the clay minerals, montmorillonite and other smectite minerals are the most useful for this purpose. The alumino- or magnesium silicate framework has a layer structure and in the crystal the layers are arranged one above the other. Each layer is negatively charged and the electric charge is neutralized by exchangeable cations, most of which are located in the interlayer space. The adsorbed organic cations and molecules are also located in the interlayer space.

Organic cationic dyes are adsorbed by the smectite minerals causing the mineral to be colored. The colored mineral may be used as a pigment for the color industry. The subject was recently reviewed Yariv S. (2001) Staining of clay minerals and visible adsorption spectroscopy of dye-clay complexes in "Organo-clay complexes and interactions" (S. Yariv and H. Cross, editors) Marcel Dekker, Inc., New York, pp. 463-566. The adsorption of these dyes takes place mainly by the mechanism of cation exchange.

Azo-dyes are used for different color applications. They are synthesized from aniline or its primary amine derivative, a second aromatic compound and sodium nitrite to yield products of the general formula  $Ar'-N=N-Ar''$ , called azo compounds. In this reaction, known as coupling, the nitrogen of the diazonium group is retained in the product.



The aromatic ring of the second compound must, in general, contain a powerfully electron-releasing group, generally  $-NHR$  or  $-NH_2$ .

There are three papers in the literature which describe the adsorption of azo-dyes by expanding clay minerals. Siffert, B. (1978) Preparation et etude spectrometrique de complexessilicates phylliteux colorants azoiques. *Clay Miner.*, pp. 13: 147-165. Siffert studied vermiculite complexes of the cationic azo-dye chrysoidine and the molecular azo-dyes *para*-dimethylaminoazobenzene, bis(*para*-dimethyl-aminophenylazo)-orthotolidine, and bis(*para*-dimethyl-aminophenylazo)Diphenyl. Depending on the pH of the system, the dye adsorption occurs either by molecular or by cation exchange mechanism.

Gabelica, Z., Valange, S., Shibata, M., Hotta, H. (2001): Stability against color fading of azo-dyes encapsulated in Ca-aluminosilicate mesoporous substraes. *Microporous and Mesoporous Materials*, 44-45: 645-652. Gabelica et al. studied the adsorption of Lithol Rubine B by the synthetic clay MCM-41.

Yermiyahu, Z., Lapides, I., Yariv, S. (2000). Adsorption of Congo-Red by montmorillonite. *Proc. Isr. Geological Soc., Annual Meeting, Ma'a lot 2000 (Abstracts)*, p. 131. Yermiyahu, et al. studied the adsorption of Congo-Red by montmorillonite. This azo-dye is adsorbed by the clay mineral although it is an anionic species.

According to the present invention it has now been discovered that azo-dyes can be formed in-situ within natural and synthetic clay minerals of the smectite family, e.g., montmorillonite.

Thus according to the present invention there is now provided a process for the preparation of a pigment which is an organo-clay complex comprising introducing an aniline derivative acidified by hydrochloric acid and a secondary aromatic compound into a smectite mineral and treating the same with sodium nitrate solution whereby an azo-dye compound is obtained in the interlayer space of the clay to form pigmented particles.

In preferred embodiments of the present invention said aniline derivative is selected from the group consisting of anilinium chloride, naphthyl ammonium chloride and benzidinium chloride and said secondary aromatic compound is selected from the group consisting of 2-hydroxy-naphthalene, 2,3-dihydroxy-naphthalene, 4-amino-2-chlorotoluene-5-sulfonic acid, 2-chloro-4-aminotoluene and 2-hydroxy-1-naphthoic acid.

While the invention will now be described in connection with certain preferred embodiments in the following examples so that aspects thereof may be more fully understood and appreciated, it is not intended to limit the invention to these particular embodiments. On the contrary, it is intended to cover all alternatives, modifications and equivalents as may be included within the scope of the invention as defined by the appended claims. Thus, the following examples which include preferred embodiments will serve to illustrate the practice of this invention, it being understood that the particulars shown are by way of example and for purposes of illustrative discussion of preferred embodiments of the present invention only and are presented in the cause of providing what is believed to be the most useful and readily understood description of formulation procedures as well as of the principles and conceptual aspects of the invention.

## EXAMPLES

The present pigments are prepared from different smectite minerals. Most of the work was carried out with montmorillonite and Laponite. The following examples and colors are related to montmorillonite.

### Example 1

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt 1-Naphthylammonium chloride was added and stirred. After two hours 2-Chloro-4-aminotoluene was added (1.0 ml of an aqueous or alcoholic

solution of 0.1 molar) and the mixture was stirred for half an hour.

2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a violet color was developed immediately. The intensity of the color increased within 24 hours. After one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

### Example 2

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt 1-Naphthylammonium chloride was added and stirred. After two hours 4-Amino-2-chlorotoluene-5-sulfonic Acid was added (1.0 ml of an aqueous or alcoholic solution of 0.1 molar) and the mixture was stirred for half an hour. 2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a red color was developed immediately. The intensity of the color increased within 24 hours. After one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

### Example 3

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt Anilinium-chloride was added and stirred. After two hours 2,3-Dihydroxynaphthalene was added (1.0 ml of an aqueous or alcoholic solution of 0.1 molar) and the mixture was stirred for half an hour.

2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a red color was developed immediately. The intensity of the color increased within 24 hours. After one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

**Example 4**

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt 1-Naphthylammonium chloride was added and stirred. After two hours 1-Naphthylammonium chloride was added (1.0 ml of an aqueous or alcoholic solution of 0.1 molar) and the mixture was stirred for half an hour.

2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a blue color was developed immediately. The intensity of the color increased within 24 hours. After one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

**Example 5**

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt 1-Naphthylammonium chloride was added and stirred. After two hours 2,3-Dihydroxynaphthalene was added (1.0 ml of an aqueous or alcoholic solution of 0.1 molar) and the mixture was stirred for half an hour.

2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a violet color was developed immediately. The intensity of the color increased within 24 hours. After one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

**Example 6**

To 20 ml of an aqueous 1% clay suspension, 1.0 ml of an aqueous solution of 0.1 molar of the salt Anilinium-hydrochloride was added and stirred. After two hours 2-Hydroxy-1-naphthoic acid was added (1.0 ml of an aqueous or alcoholic solution of 0.1 molar) and the mixture was stirred for half an hour.

2.0 ml of aqueous solution of 0.1 molar  $\text{NaNO}_2$  was added, and a red color was developed immediately. The intensity of the color increased within 24 hours. After



one week the solid fraction was washed three times with distilled water and was separated from the supernatant by centrifugation.

It will be evident to those skilled in the art that the invention is not limited to the details of the foregoing illustrative examples and that the present invention may be embodied in other specific forms without departing from the essential attributes thereof, and it is therefore desired that the present embodiments and examples be considered in all respects as illustrative and not restrictive, reference being made to the appended claims, rather than to the foregoing description, and all changes which come within the meaning and range of equivalency of the claims are therefore intended to be embraced therein.

**WHAT IS CLAIMED IS:**

1. A process for the preparation of a pigment which is an organo-clay complex comprising introducing an aniline derivative acidified by hydrochloric acid and a secondary aromatic compound into a smectite mineral and treating the same with sodium nitrite solution whereby an azo-dye compound is obtained in the interlayer space of said clay to form pigmented particles.
2. A process according to claim 1 wherein said aniline derivative is selected from the group consisting of anilinium chloride, naphthyl -ammonium chloride and benzidinium chloride.
3. A process according to claim 1 wherein said secondary aromatic compound is selected from the group consisting of 2-hydroxy-naphthalene, 2,3-dihydroxy-naphthalene, 4-amino-2-chlorotoluene-5-sulfonic acid, 2-chloro-4-aminotoluene and 2-hydroxy-1-napthoic acid.

For the Applicant

**WOLFF, BREGMAN AND GOLLER**

by:

*G. Goller*